



Technical Data Sheet Acid Resistance Bricks & Tiles As Per IS-4860:1968

S.No.	Product Name	Water Absorption Minimum % by 2h Boiling Test	Clod Crushing Strength (Kg/ Cm ²) Min.	Flexural Strength (Kg/ Cm ²) Min.	Resistance To Acid Max. (%)
1	Class- I	<2	>700	>100	<1.5
2	Class- II	<4	>500	>70	<4