



Technical Data Sheet Hot Face Insulation Bricks

S. No.	Product Name	Service Temperature (°C)	Apparent Porosity (%)	Bulk Density (gm/cm ³)	CCS (kg/cm ²)	Thermal Conductivity in Kcal/m/hr/deg.c at 600°C HF
1	HFI	1250°C	60	0.9	15	0.25