



Technical Data Sheet Mullite Bricks

S. No.	Product Name	Chemical Analysis (wt%)		Apparent Porosity (%)	Bulk Density (g/cc) Min.	CCS (kg/cm ²)	PLC (%)	PCE (°C/OC) Min.	RUL (T _a ⁰ C)
		Al ₂ O ₃	Fe ₂ O ₃						
1	AL-70MUL	67- 69	0.3- 0.7	19- 21	2.50- 2.70	600- 800	±0.5 at 1500°C/ 2h	37	1650- 1700